




Solo Europe
Tower Close
St. Peters Industrial Park
Huntingdon
Cambridgeshire
PE29 7BZ
United Kingdom
Attn: Alastair Reed

Date: 9 August 2007

Testing conducted between 27/03/2007 and 29/03/2007


Sample Description: Paper Cups**Details of Sample:** A sample of plastic lined white paper cups.**Tests Required:** Overall Migration Testing**Results:**

Simulant	Conditions	Migration
3% Acetic Acid	30 minutes at 70°C followed by 3.5 hours at 40°C	0.3 mg/dm ²
10% Ethanol	30 minutes at 70°C followed by 3.5 hours at 40°C	<0.1 mg/dm ²

The material was tested in accordance with the requirements of the Plastic Materials and Articles in Contact with Food Commission Directive 2002/72/EC following Methods BSEN 1186:2002.

The Regulations require that no plastic material shall be capable of transferring its constituents to food with which it may come into contact in quantities exceeding the appropriate limit. For the material the appropriate limit is 10 mg/dm².

The migration from the material was less than the maximum permitted by the Regulations.

Signed 

Melvyn Wolff
Hardlines Technical Manager

*** End of Report ***

This document is issued by the Company subject to its General Conditions of Service available on request and accessible at www.sgs.com. Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated: (a) the results shown in this document refer only to the sample(s) tested and (b) such sample(s) are retained for 30 days only. This document cannot be reproduced except in full, without prior approval of the Company. Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation